




INVESTOR IN PEOPLE

PCT/EP04/1738




The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

P. Mahoney


Dated

20 January 2004

**PRIORITY
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Best Available Copy



The
Patent
Office

07FEB03 E783280-1 D02914
P01/7700 0.00-0302840.4 The Patent Office

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

Cardiff Road
Newport
South Wales
NP9 1RH

1. Your reference

SN134

2. Patent application number

(The Patent Office will fill in this part)

0302840.4

7 FEB 2003

3. Full name, address and postcode of the or of each applicant (underline all surnames)

DOW CORNING CORPORATION
Midland
Michigan 48611
USA

Patents ADP number (*if you know it*)

8506040002

T-1

If the applicant is a corporate body, give the country/state of its incorporation

USA/Michigan

4. Title of the invention

PROCESS FOR MAKING SILICONE EMULSIONS

5. Name of your agent (*if you have one*)

P V Davies

"Address for service" in the United Kingdom to which all correspondence should be sent (*including the postcode*)

DOW CORNING LIMITED
Intellectual Property Department
Cardiff Road
Barry
CF63 2YL

Patents ADP number (*if you know it*)

7804594001

T-1

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (*if you know it*) the or each application number

Country

Priority application number
(*if you know it*)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (*Answer 'Yes' if:*

Yes

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description

7

Claim(s)

2

Abstract

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

1

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

1 fee sheet

11. I/We request the grant of a patent on the basis of this application.

Signature

P V Davies

Date

06/02/03

12. Name and daytime telephone number of person to contact in the United Kingdom P V Davies 01446 723505

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

PROCESS FOR MAKING SILICONE EMULSIONS

Field of the Invention

5 [0001] This invention relates to the production of silicone oil in water emulsions, useful for example in toiletry and cosmetic products such as shampoos, conditioners and skin creams, textile process additives such as hydrophilic/hydrophobic modifiers and softeners, and automotive care and household cleaning products. In particular it relates to the production of emulsions of organo-functional polysiloxanes, that is polysiloxanes containing
10 functional organic groups such as amine, amide, epoxide, alcohol or thiol groups.

Background to the Invention

[0002] US-A-6239211 describes the production of emulsions of amino-functional
15 polysiloxanes by emulsifying low molecular weight or cyclic silicones and then reacting with amino-silanes at high temperature. US-A-6090885 describes incorporation of amine functionality in linear polyorganosiloxane in the presence of cationic surfactant. US-A-4600436 describes an aminofunctional silicone emulsion prepared from water, emulsifier, diorganopolysiloxane fluid, aminofunctional silane, and optionally a polymerisation catalyst,
20 by emulsion polymerisation, and teaches that the emulsion polymerized polysiloxane emulsion can be stripped of cyclic or other low molecular weight siloxanes from which it was prepared.

[0003] For use in the personal care industry, it is preferred that emulsions contain
25 reduced quantities of the cyclic siloxane octamethylcyclotetrasiloxane (D4) due to its classification as a reproductive hazard. It is an object of the present invention to prepare emulsions of organo-functional polysiloxanes, especially amino-functional polysiloxanes, containing a lower level of D4 than the emulsions of amino-functional polysiloxanes prepared by emulsion polymerisation as described above, without needing stripping.

Summary of the Invention

[0004] A process according to the invention for the preparation of an emulsion of an organo-functional polysiloxane comprises emulsifying a silanol-functional polysiloxane (I) in water, adding an organofunctional silane of the formula $X-A-Si(R)_n(OR')_{3-n}$ (II), where X represents an organic functional group; A represents a divalent organic linkage; each R represents a hydrocarbyl or substituted hydrocarbyl radical; each R' represents hydrogen or an alkyl or acyl group; and $n = 0, 1$ or 2 , to the aqueous phase of the resulting emulsion and reacting the $-OR'$ groups of (II) with the silanol groups of the polysiloxane (I) to form the organo-functional polysiloxane.

Detailed description of the Invention

[0005] The silanol-functional polysiloxane (I) is preferably a substantially linear polydiorganosiloxane fluid such as polydimethylsiloxane, although branched polysiloxanes can also be used. The silanol groups are preferably terminal groups on the polysiloxane chain. The polysiloxane fluid can for example have a viscosity of at least 0.02 Pa.s up to 1000 Pa.s (20 up to 1000000 cps), preferably 0.5 to 40 Pa.s. Most preferably the silanol-functional polysiloxane (I) has a molecular weight that is near the desired final molecular weight of the desired organofunctional polysiloxane. Both the emulsification of (I) and the reaction with the organofunctional silane (II) are preferably carried out under conditions which do not promote polycondensation of the polysiloxane (I).

[0006] The silanol-functional polysiloxane (I) is preferably mechanically emulsified in water. This emulsification step is preferably carried out in the absence of any basic or acidic catalyst for silanol polycondensation. The silanol-functional polysiloxane (I) is preferably emulsified continuously, although it can alternatively be emulsified batchwise. In one preferred procedure the silanol-functional polysiloxane (I), at least one surfactant and water are continuously fed to a high shear mixer in such proportions as to form a viscous oil in water emulsion which is continuously withdrawn from the mixer and is diluted before addition of the organofunctional silane (II).

[0007] The amount of surfactant is generally at least 0.2% by weight based on the silanol-functional polysiloxane (I), preferably at least 0.5%, for example from 2% up to 10 or 20%. The amount of water present, including any water present in the surfactant composition, is generally at least 0.5% based on the polysiloxane fluid, preferably at least 1% up to 10 or 20% or even 30%. The polysiloxane content of the mixture fed into the high shear mixer is preferably from 70 to 99% by weight, most preferably 80 to 98%. At these proportions the polysiloxane, surfactant and water form a non-Newtonian "thick phase" emulsion, which has a very high viscosity at low shear rates, but mixtures with this high polysiloxane content emulsify more readily to small particle size than a more dilute mixture.

[0008] Mechanical emulsion via such a "thick phase" is most effectively carried out as a continuous process. A particularly preferred procedure is described in WO-A-02/42360. The high shear mixer can for example be an in-line, dynamic rotor/stator device such as those sold under the Trade Marks "TK Products Homomic Line Mill" or "Bematek" or "Greerco" or "Ross", often referred to as a colloid mill, or a rotary disc mixer of the type described in JP-A-2000-449, or a twin screw compounder of the type used for plastics extrusion.

[0009] The surfactant used for emulsification of the silanol-functional polysiloxane (I) is preferably one or more non-ionic surfactant. Examples of non-ionic surfactants include polyoxyalkylene alkyl ethers such as polyethylene glycol long chain (9-22C, especially 12-14C) alkyl ether, polyoxyalkylene sorbitan ethers, polyoxyalkylene alkoxyate esters, polyoxyalkylene alkylphenol ethers, ethylene oxide propylene oxide copolymers, polyvinyl alcohol, glyceride esters and alkylpolysaccharides. Non-ionic surfactants are generally unlikely to catalyse polycondensation of the polysiloxane.

[0010] Ionic surfactants such as cationic, amphoteric and/or anionic surfactants can alternatively be used. Examples of cationic surfactants include quaternary ammonium salts such as 8-22C alkyl trimethyl ammonium halides, 8-22C alkyl dimethyl benzyl ammonium halides or di(8-22C alkyl) dimethyl ammonium halides. Examples of suitable amphoteric surfactants include cocamidopropyl betaine, cocamidopropyl hydroxysulphate, cocobetaine, sodium cocoamidoacetate, cocodimethyl betaine, N-coco-3-aminobutyric acid and imidazolinium carboxyl compounds. Examples of anionic surfactants include alkyl sulfates

such as lauryl sulfate, polymers such as acrylates/C₁₀₋₃₀ alkyl acrylate crosspolymer, (6-20C alkyl) benzenesulfonic acids and salts, the sulfate esters of monoalkyl polyoxyethylene ethers, sulphonated glyceryl esters of fatty acids, and salts of sulphonated monovalent alcohol esters. Some anionic surfactants such as sulphonic acids have catalytic activity for condensation polymerisation of silanol-functional polydiorganosiloxanes. The catalytic activity can be suppressed by a neutralising agent such as an organic amine, for example triethanolamine, or an inorganic base such as sodium hydroxide. In general we prefer to avoid use of anionic surfactant unless it is desired to emulsify the silanol-functional polysiloxane (I) in a process including controlled polymerisation of (I).

[0011] If the silanol-functional polysiloxane (I) is emulsified as a "thick phase", it is preferably diluted before addition of the organofunctional silane (II). The emulsion preferably has a concentration of 20-75% by weight polysiloxane (I) at the time it is reacted with the organofunctional silane (II). The "thick phase" can be diluted with water alone, or with a mixture of water and surfactant. The surfactant used in dilution can be of any of the types described above. The surfactant may be chosen to be the most compatible with the organofunctional silane (II). For example a cationic surfactant can be used in the dilution step when the organic functional group of (II) is an amino group. Alternatively, non-ionic surfactants are generally suitable for dilution.

[0012] The organofunctional silane of the formula $X-A-Si(R)_n(OR')_{3-n}$ (II) is most preferably an aminosilane. The invention is particularly suitable for the production of emulsions of amino-functional polysiloxane useful for example in toiletry and cosmetic products such as shampoos and skin creams. The organic functional group X is thus preferably a primary, secondary or tertiary amine group, for example $-NH_2$ or $-NHC_2H_5$, or can be a group including both primary and secondary amino such as $-NHC_2H_4NH_2$.

[0013] The organic functional group X can alternatively be an amide, epoxide, alcohol or thiol group.

[0014] The groups OR' in (II) are preferably alkoxy groups, that is R' is preferably an alkyl group, more preferably 1-4C alkyl. The group R, if present, is also preferably 1-4C

alkyl. Most preferably each group R' of silane (II) is a methyl radical. We have found that methoxy silanes are more reactive than ethoxy or higher alkoxy silanes, and aminosilanes containing methoxy groups are thus easier to incorporate into the polysiloxane. Particularly preferred examples of organofunctional silanes (II) include 3-aminopropyl trimethoxy silane and 3-(2-aminoethylamino)propyl trimethoxy silane.

[0015] The molar ratio of silanol groups of (I) to Si-bonded alkoxy or other groups OR' of organosilane (II) is preferably in the range (0.4-1.5:1). In many cases it is preferred that the molar ratio of silanol groups of (I) to Si-bonded alkoxy groups of aminosilane (II) is less than 1:1, so that the main reaction taking place is capping of the silanol-functional polysiloxane (I) by the amino- or other organo-functional alkoxysilane (II). Molar ratios of silanol groups of (I) to Si-bonded alkoxy groups of aminosilane (II) greater than 1:1 may be preferred if it is desired that chain extension polymerization of (I) should also take place to produce an organo-functional polysiloxane of greater degree of polymerisation than the starting silanol-functional polysiloxane (I).

[0016] When the organofunctional silane (II) is an amino- or amido-functional silane, the reaction with polysiloxane (I) is preferably carried out in the presence of a cationic surfactant is added to the emulsion no later than the addition of the organofunctional silane (II). When the polysiloxane (I) is emulsified as a "thick phase" and is diluted before reaction with the organofunctional silane (II), the cationic surfactant can be present in the water in the dilution step as described above. The cationic surfactant can alternatively be added with the aminosilane (II), or can be added to the dilute emulsion before addition of (II). The amount of cationic surfactant added can for example be 1 to 10% based on the total weight of siloxane reagents.

[0017] A base is preferably added to the emulsion to catalyse the reaction of the -OR' groups of (II) with the silanol groups of the polysiloxane (I). The base can be added to the emulsion before, together with or after the organofunctional silane (II). The base is preferably an inorganic base such as sodium hydroxide or potassium hydroxide, or alternatively can be an amine such as triethanolamine. The amount of base is preferably that required to obtain pH of 9-13, most preferably 11-12.

[0018] The organofunctional silane (II) and the silanol-functional polysiloxane (I) are preferably reacted at a temperature below 40°C, most preferably below 30°C, for example at ambient temperature of 10-25°C. We have found that a low temperature of reaction between (I) and (II) is particularly effective in producing an emulsion having a low D4 level. The time of reaction can for example be 0.5 to 24 hours.

[0019] The emulsion of organo-functional polysiloxane produced by the process of the present invention generally contains less than 2% by weight cyclic polysiloxane, in particular less than 2% D4, based on the total weight of polysiloxane in the emulsion. When the temperature of reaction of (I) and (II) is kept below 30°C, emulsions of aminosiloxane containing less than 1% D4 can be produced.

[0020] The emulsions of the present invention have particular advantage for personal care applications, for example in toiletry and cosmetic products such as shampoos and skin creams, where there is a particular demand for emulsions of low D4 content, but are also advantageous for use in textile treatment, for example as fabric softeners, and for automotive care.

[0021] The invention is illustrated by the following Example, in which parts and percentages are by weight.

Example 1

[0022] 60 parts of a substantially linear hydroxy-endblocked polydimethylsiloxane of viscosity 4000 mPa.s. was emulsified with 2.5 parts Renex 30 (Trade Mark) nonionic surfactant and 1.33 parts water via a continuous process using a high shear mixer as described with reference to Figure 1 of WO-A-02/42360. The resulting thick phase emulsion was diluted with water batchwise to 50% silicone in a stirred reactor, and 5.87 parts Arquad 16-29 (Trade Mark) 30% active cationic surfactant was added. 0.5 parts 50% aqueous sodium hydroxide and 7 parts 3-(2-aminoethylamino)propyl trimethoxy silane were added. The

emulsion was reacted for 6 hours at room temperature (23°C). An aminosiloxane emulsion of particle size 200 nm was obtained. The D4 content of the final emulsion comprised 0.7% of the silicone phase.

- 5 [0023] Application testing on hair has shown equivalent performance to a commercial aminosiloxane emulsion of D4 content 6.6%.

CLAIMS

1. A process for the preparation of an emulsion of an organo-functional polysiloxane comprising emulsifying a silanol-functional polysiloxane (I) in water, adding an organofunctional silane of the formula $X-A-Si(R)_n(OR')_{3-n}(II)$, where X represents an organic functional group; A represents a divalent organic linkage; each R represents a hydrocarbyl or substituted hydrocarbyl radical; each R' represents hydrogen or an alkyl or acyl group; and $n = 0, 1$ or 2 , to the aqueous phase of the resulting emulsion and reacting the $-OR'$ groups of (II) with the silanol groups of the polysiloxane (I) to form the organo-functional polysiloxane.
2. A process according to Claim 1, wherein the silanol-functional polysiloxane (I) is mechanically emulsified in water in the absence of any basic or acidic catalyst for silanol polycondensation
3. A process according to Claim 2, wherein the silanol-functional polysiloxane (I) is emulsified in the presence of a non-ionic surfactant.
4. A process according to any of Claims 1 to 3, wherein the silanol-functional polysiloxane (I), at least one surfactant and water are continuously fed to a high shear mixer in such proportions as to form a viscous oil in water emulsion which is continuously withdrawn from the mixer and is diluted before addition of the organofunctional silane (II).
5. A process according to any of Claims 1 to 4 wherein the organic functional group X of silane (II) is an amino group.
6. A process according to any of Claims 1 to 5 wherein each group R' of silane (II) is a methyl radical.

7. A process according to Claim 6 wherein the organofunctional silane is 3-aminopropyl trimethoxy silane.
8. A process according to any of Claims 1 to 7 wherein a cationic surfactant is added to the emulsion no later than the addition of the organofunctional silane (II).
9. A process according to any of Claims 1 to 8 wherein a base is added to the emulsion to catalyse the reaction of the -OR' groups of (II) with the silanol groups of the polysiloxane (I).
10. A process according to any of Claims 1 to 9 wherein the organofunctional silane (II) and the silanol-functional polysiloxane (I) are reacted at a temperature below 40°C.
11. An emulsion of an organo-functional polysiloxane prepared by the process of any of Claims 1 to 10, characterised in that the emulsion contains less than (2)% by weight cyclic polysiloxane based on the total weight of polysiloxane in the emulsion.

THE PATENT OFFICE
25 FEB 2004
Received in Patents
International Unit

PCT/EP2004/001738

